

CAD-COLOR® SuperTEK® Sublistop™ Printable Heat Transfer Vinyl

Application Instructions

1-Color Application Instructions

Time: Tack for 5 seconds, peel warm, cover and seal 5 seconds.
Temperature: 280-300°F/ 138-150°C
Pressure: Medium (#6 on Hotronix)

Care Instructions

We recommend COLD wash only for this product.
 Machine wash inside-out using mild detergent.
 Do not use bleach. Dry at a normal dryer setting on household machines. Do not dry clean.

Material/Fabric Compatibility

- 100% Cotton
- 100% Polyester
- 100% Preshrunk Cotton
- Cordura®
- Cotton/Poly Blends
- Leather
- Lycra®/Spandex Blends
- Neoprene
- Nylon

Heated Lower Platen Application

Lower Platen: 320°F
Upper Platen: 250°F
Time: 12-15 seconds (depending on thickness of garment)
Pressure: Medium

Storage

Store in a cool and dry area around 65 to 70 degrees Fahrenheit with 50% relative humidity. Keep away from direct heat, sunlight and humidity. Recommended shelf life is one year.

Cutter Guidelines

Cutter	Blade	Force	Offset	Speed
Roland® GX-24	45°	80-90g	.25	30cm/s
Roland® VP-300	45°	80-90g	.25	30cm/s
Roland® SP-300	45°	80-90g	.25	30cm/s
Roland® XC-540	45°	80-90g	.25	30cm/s

Always test cut prior to any production run. For optimal cutting and weeding, maintain a line thickness of at least 1/16" for lettering & logos.

PARA MÁS INFORMACIÓN

Bogotá
 Calle 71B No. 28 – 36, Barrio Alcázares
 ventas@signproducts.com.co

Medellín
 Calle 32F No. 76-56, Barrio Laureles
 asimedellin@signproducts.com.co

www.signproducts.com.co